

# YS-M305/XXX TOP QUALITY HYDRO-OIL - WAX EFFECT

## BEST FOR

General use for exterior. Exterior grade wood stain look. Sidings, wooden structure, garden furniture. Suitable for hardwood\* and softwood.

\*Apply 1 coat of YS---C100/--XXX as bonder for best durability.

## INFORMATION

This product provides a high build and fast drying time. It contains wood preservatives, e.g. IPBC. The product isn't film-forming, so sanding is no more required.

## INSTRUCTIONS

The wood must be dry (12-17% humidity, preferably at more than 15°C/60°F). Clean the wooden surface from traces of grease, wax or dirt by sanding with 150-180 grit sandpaper.

## DRYING TIME - OVERCOATING

Drying time between coats: 3-4 h according to drying temperature, film thickness and ventilation (for tunnel drying, contact the supplier).

\*Dust free: 30 minutes

\*Touch free: 1 hour

\*Sandable: not required

\*Stackable: 24-48 hours

\*Final curing: 24-48 hours

\*At ideal conditions

## OVERCOATING

Sanding is not necessary to overcoat the surface already treated with YS---M305 since the product is self-consuming.

## EQUIPMENT

- With gravity cup gun, use 1.9 to 2.5 tip size.
- With HVLP equipment, use 1.9 to 2.2 tip size.
- With brush.
- With roller.

Application equipment must be cleaned with water immediately after use.

## CATALYST

If desired, catalyze the product at 5% with YC---M404. Once catalyzed, the product has a pot-life of 3-4 hours. No need of thinning the product with water unless desired. Up to 10% of water is allowed.

## DURABILITY

The product must be pigmented in order to express the best outdoor resistances. Ask for more info to your Renner specialist.

## MAINTENANCE

*Coating in good condition (every 3-6 months):* wash with warm water and soft cloth. Apply T.Clean RR1050 Neutral Detergent - T.Top+ RR1250 Brightener kit. Do not use alcohol or aggressive solvent.

*Coating with light aging damages (climate condition will define the maintenance frequency):* use T.Clean RR1050 Neutral detergent and a micro-fiber cloth to remove traces of dirt or oil. Do not use alcohol or aggressive solvents. Let dry very well. Clean thoroughly with a sorghum (natural or synthetic) still brush. Apply 1-2 coats by brush of YS---M305/--XXX coloured.



### Storage

5-35° C

41-95° F



### Painting

>15° C (60° F)

best @20-25° C (68-77° F)



### 1-2K @5% YC---M404

6 Oz/Gal



### Application

HVLP / Gravity cup gun /  
Brush / Roller



### Yield

Approx. 12-20 m<sup>2</sup>/L

490-730 ft<sup>2</sup>/Gal



### Final drying time

24-48 h at room temperature



### Qty per coat

60-100 g/m<sup>2</sup>

3-4 wet mils



### No. of coats

Max 3



### Availability

Every color



### Gloss Level

Matt