

TRESPA® TOPLAB® BASE

Cleaning

Trespa® TopLab® BASE panels are specifically designed for interior applications. Their integrated decorative surface is designed for intensive use. It is impact, scratch and wear resistant. Panels are easy to keep clean and as they do not absorb or retain moisture they can be cleaned frequently, using standard cleaning agents and certain disinfectants.

General

The surfaces of Trespa® TopLab® BASE can be easily cleaned with a dry or damp cloth and, if necessary, a mild household cleaner. Wipe damp surfaces with an absorbent cloth. Use of concentrated acid, caustic or abrasive cleaning agents is not recommended.

Remove severe soiling

Severely dirty surfaces or areas where normal soiling* has built up over a long period of time are easy to clean with hot water and an interior detergent or soap-based cleaning agent, applied with a sponge or soft nylon brush. Apply the diluted cleaning agent to the surface and leave it to soak. The rinse off with clean water and dry with an absorbent cloth.

** dust, pencil, ball pen, ink, coffee, tea, fruit juice, lipstick, grease, nicotine stains, shoe polish, urine, soap residues, lime scale, water-soluble paints and adhesives.*

Occasionally, it may be necessary to remove old stains or very stubborn marks with a liquid cleaner containing very fine polishing particles (attention: the surface may be damaged that way) or with bleach. Wash the surface down thoroughly afterwards with clean water and dry with an absorbent cloth.

Removing special staining

- Solvent-based varnishes and adhesives (nail varnish, rubber stamp ink and aerosol paint), tar and other soluble but strong stains should be removed with organic solvents such as acetone, white spirit, turpentine or petroleum.
- Remove wax from candles or crayons immediately with water and a mild household cleaning agent. Dried wax stains may first have to be scraped off with a wooden or plastic spatula and the remainder removed with an organic solvent.
- Two part paint or adhesive, synthetic resin and the like should be removed immediately with water or an organic solvent. Once these products have set, they cannot be removed without damaging the surface.
- Rub silicone off dry or use a silicone remover.
- Limescale can be removed with acidic cleaning agents containing approximately 10 % acetic acid or citric acid. The manufacturer's instructions must be strictly followed. Rinse surfaces and edges very thoroughly!

Frequent cleaning

The recommended method for everyday cleaning of Trespa® TopLab® BASE wall cladding and partitions in shower and changing cubicles or sanitary units is warm water with a mild universal cleaning agent applied with a sponge or soft nylon brush. This is the ideal way to remove most light, recent soiling.

Wipe damp surfaces with an absorbent cloth. Use of concentrated acid, caustic or abrasive cleaning agents is not recommended.

Using disinfectants

Both the decorative surface and core of Trespa® TopLab® ^{BASE} are highly resistant to most commonly-used disinfectants such as:

- alcohol, preferably 60-70 % solution in water.
- aldehydes, although not in, or in combination with, quaternary ammonia compounds.
- chlorine separating compounds. However, long term use of these products can cause certain pigments to fade.
- phenols, not to be used for kitchen disinfection.
- peroxide compounds (hydrogen peroxide and organic peracids).
- quaternary ammonia compounds.

Some manufacturers offer products containing both cleaning and disinfecting components. These are known as detergent sanitizers, and are intended for simultaneous cleaning and disinfection of light to medium soiled surfaces in rooms where there is no great risk of infection.

Caution

Always follow the manufacturer's instructions carefully when using any cleaning agent or disinfectant. Using a combination of products may cause unwanted chemical reactions which produce harmful gases. When surfaces have been cleaned with aggressive cleaning agents, they should be rinsed well to dilute the cleaning agent and prevent it from drying on the panel surface.

DISCLAIMER

This is a print generated by you from www.trespa.info ("Website"). By accessing the Website and printing this document you have accepted the Terms of Use of the Website. Please refer to the Website for all conditions that apply to this document. The system shown in this document may not be suitable for all applications and jurisdictions. We provide you with testing data and certification information for informational purposes only. We strongly recommend that you or any other user of this document obtains advice regarding compliance with design requirements, applicable codes, laws and regulations, and test standards from independent experts. Please check your local codes and design requirements for proper use. Trespa will not accept any liability in relation to your use of this document.

All intellectual property rights, including copyrights and other rights regarding the content of the Website and this print generated from the Website (including logos, trademarks, service marks, software, databases, audio, video, text and photographs) are owned by Trespa and/or its licensors. ® Trespa, Meteon, Pura, Pura NFC, Athlon, Izeon, TopLab, TopLab^{PLUS}, TopLab^{PLUS ALIGN}, TopLab^{ECO-FIBRE}, TopLab^{VERTICAL}, TopLab^{BASE}, Trespa Essentials and Mystic Metallics, Virtuon and Volkern are registered trademarks of Trespa.

All oral and written statements, offers, quotations, sales, supplies, deliveries and/or agreements and all related activities of Trespa are governed by the Trespa General Terms and Conditions of Sale (Algemene verkoopvoorwaarden Trespa International B.V.) filed with the Chamber of Commerce (NL) on 9 May 2023 under number 24270677, which can be found on and downloaded from the Trespa website, www.trespa.com.

All oral and written statements, offers, quotations, sales, supplies, deliveries and/or agreements and all related work of Trespa North America, Ltd. are governed by the Trespa North America General Terms and Conditions of Sale, which can be found on and downloaded from the Trespa website, www.trespa.com/documentation. A copy of these general conditions of sale will be provided free of charge on request. All general terms and conditions other than the conditions mentioned above are dismissed and do not apply, regardless of whether such terms and conditions are referred to on requests for offers, offer confirmations, stationery and/or other documents of the other party, even if Trespa does not expressly object to such terms and conditions.